

TEMMER

LONDON • ATLANTA • ISTANBUL

Physical Test Crema Lucida	ASTM	Imperial	Metric
Absorption by weight	ASTM C97	0.17 %	.017%
Density	ASTM C97	168.1lb/ft ³	2693kg/m ³
Compressive Strength	ASTM C170 PPW	17 250 Psi	118.9MPa
	ASTM C170 PPD	17 920 Psi	123.6 MPa
	ASTM C170 LLW	17 930 Psi	123.6 MP
	ASTM C170 LLD	17 240 Psi	118.8 MPa
Modulus of Rupture	ASTM C880 PPW	1 390 Psi	9.6 MPa
	ASTM C880 PPD	1 120 Psi	7.7 MPa
	ASTM C880 LLW	1 170 Psi	8.1 MPa
	ASTM C880 LLD	870 Psi	6.0 MPa
Abrasion Resistance	ASTM C1353	35.3 lw	

PPW = Perpendicular Wet

PPD = Perpendicular Dry

LLW = Parallel Wet

LLD = Parallel Dry